



SuperForm™
MAX+25

Density (lbs/ft³): 1.8

T 877.627.3555
F 403.627.3553
E info@superformicf.com

superformicf.com

CAN/ULC-S701: Standard for Thermal Insulation, Polystyrene, Boards & Pipe Covering

Property	ASTM TEST	UNITS	TYPE 3
Thermal Resistance Values® Minimum @ 24°C (75°F)	C518	m2 • °C/ (W • 26.99mm) RSI Value	0.88
		ft2 • hr • °F/(BTU • in) R-Value	5
Water Vapor Permeance Maximum	E96	ng/(Pa • s • m2)	130
		perms	2.25
Dimensional Stability Maximum	D2126 7 Days @ 70± 2°C	% linear change	1.5
Flexural Strength Minimum	C203 Procedure B	kPa	345
		Psi	50
Water Absorption Maximum	D2842	% by volume	2.0
Compressive Strength Minimum @ 10% Deformation	D1621 Procedure A	kPa	175
		Psi	25
Limiting Oxygen Index Minimum	D2863	%	24

NOTE: Values quoted are maximum values for (26.99mm) thick samples with natural skins intact. Lower values will result for thicker materials. Where water vapor permeance is a design issue, consult manufacturer.

Applications: Wall, Ceiling, Perimeter, Below Grade, Floor Insulation, Roofing,
EIFS, Structural Insulated Panels (SIP), Precast Floor & Wall Panels